



Typical Properties of

Tecaform® AH ELS

Electro Conductive Acetal

Process: Extruded

Property	Test Method	Unit	Value
Specific Gravity	D792	--	1.41
Tensile Strength	D638	psi	6,090
Tensile Modulus	D638	psi	261,000
Elongation	D638	%	11
Flexural Strength	D790	psi	8,120
Flexural Modulus	D790	psi	217,000
Compressive Strength	D695	psi	3,625
Compressive Modulus	D695	psi	217,000
Hardness, Rockwell	D785	--	N / A
Hardness Durometer	--	--	N / A
Izod Impact (notched)	D256	ft. lb of notch	N / A
Coeff. of Friction (Dynamic)	--	dry v.s steel	N / A
Coeff. of Linear Therm. Expan.	E831/ D696	in./in./°F	N / A
Continuous Use Temperature	--	°F	210
Heat Deflection Temperature	D648	°F	N / A
Glass Transition Temperature	D3418	°F	145
Melting Point	D3418	°F	336
Thermal Conductivity	E1530-11	BTU in/hr ft ² °F	N / A
Dielectric Strength	D149	Volts/mil	N / A
Surface Resistivity	EOS/ESD 511.11	ohm/square	<10 ⁴
Flammability	UL94	--	HB
Water Absorption, 24 hrs.	D570	% by weight	0.05
Water Absorption, Saturation	D570	% by weight	0.2
Limiting PV (4:1 Safety Factor)	--	--	N / A
K-Factor	--	--	N / A
FDA Compliance	--	--	No

Note: The data provided is for reference purposes only. Additional testing may be required for design specifications or quality control.
All values at 73 F unless otherwise stated.